

ITALVELLUTI

SCHEMA TECNICA TECHNICAL CARD

Data / Date

09.06.14

Articolo / Article / Tkanina	Pixel
Composizione / Composition / Kompozycja	74% PL 20%CO 5% PC 1% AF
Peso Gr/mtl / Weight Grs/lmt / Waga gr/mtb	780
Altezza cm / Width cms / Szerokość cm	138/140

Odporność na ścieranie

Test Martindale

Colour degradation after 3000 rubs: 4/5

UNI EN ISO 12947 - 2

40.000 Giri / Rubs / **Cykli**

EN 14465, appendix A

Solidità Luce / Colour Fastness to light / **Odporność kolorów na światło**

UNI EN ISO 105-B02

4/5

Blue Scale 1/8

Solidità Sfregamento / Colour Fastness to rubbing / **Odporność kolorów na pocieranie**

UNI EN ISO 105-X12

4

Secco / Dry / **Sucho**

Gray Scale 1/5

3/4

Umido / Wet / **Mokro**

Odporność na Pilling

Test Pilling

UNI EN ISO 12945-2

Degradation average photographic scale 1/5:

4/5

Manutenzione / Maintenance



Note/Notes: Dimensional stability to dry washing (UNI EN ISO 3175)

warp: +/- % weft: +/- %

Dimensional stability to washing (UNI EN ISO 6330)

warp: +/- % weft: +/- %

* The results are tested in the laboratory and they must be considered as indicative.

ITALVELLUTI Polska Sp. z o.o.
33-386 Podegrodzie, Brzezna 495,
tel./fax: 18 446 07 84
e-mail: italvelluti@italvelluti.pl
www.italvelluti.pl

ITALVELLUTI
the art of italian fabrics